


PERFILES LAMINADOS EN CALIENTE

PERFIL ANGULAR LADOS IGUALES INOXIDABLE

A	A	E	KG/MTS
20	20	3	0,915
25	25	3	1,16
30	30	3	1,62
35	35	3	1,84
40	40	4	2,516
50	50	5	3,92
60	60	6	5,636
70	70	7	7,68
80	80	8	10,046
100	100	10	15,6



PERFIL ANGULAR LADOS DESIGUALES INOXIDABLE

A	B	E	KG/MTS
30	20	4	1,47
40	20	4	1,8
50	30	5	3
60	40	6	4,51
80	40	6	5,47

